

S11 1 PN='JP 59219328'
? t11/7/1

11/7/1
DIALOG(R)File 350:Derwent WPIX
(c) 2003 Thomson Derwent. All rts. reserv.

004196007

WPI Acc No: 1985-022887/198504

Mfr. of highly polymerised polyester with low acetaldehyde content - by solid phase polymerisation with heat of pre-crystallised polyester previously subjected to moisture conditioning

Patent Assignee: TOYOBO KK (TOYM)
Number of Countries: 001 Number of Patents: 001
Patent Family:
Patent No Kind Date Applicat No Kind Date Week
JP 59219328 A 19841210 JP 8394464 A 19830528 198504 B

Priority Applications (No Type Date): JP 8394464 A 19830528

Patent Details:

Patent No Kind Lan Pg Main IPC Filing Notes
JP 59219328 A 6

Abstract (Basic): JP 59219328 A

Method comprises subjecting a polyester having ethylene terephthalate units as principal repeat units, whose intrinsic viscosity is 0.4 or more and density is 1.35 or less, to (1) moisture conditioning so that the moisture content is at least 0.2 wt%, (2) a process of pre-crystallisation at 140 deg.C or higher, and (3) subjecting the resultant to polymerisation at a solid phase at a temp. of 180-240 deg.C in an inert gas atmos. or reduced pressure.

ADVANTAGE - The content of acetaldehyde in the resulting pellet can be reduced quickly and effectively. The highly polymerised polyester prepd. by this method is suitable for packing material of foodstuff, medicinal preps. etc.

O/O

Derwent Class: A23

International Patent Class (Additional): C08G-063/26